



J D Jones & Co (P) Ltd



Pacmaan[®] NA 785

Novoloid fibre packing impregnated with PTFE and break-in lubricant in interlock braid

- Pure novoloid fibres exhibit the strength of aramid and chemical resistance of PTFE/graphite
- A multipurpose plant-wide packing for the pulp and paper industry
- A thorough impregnation of PTFE provides low friction operations and a dense packing without any leak paths
- A non-staining and non-abrasive packing—can be used for high speed applications

Available in rope and ring form

Service Media and Conditions	Chemicals, mild acids, alkali, pulp and paper applications, liquor, water, sewage etc
Temperature	-100°C to 260°C
Pressure	100 bar (static), 30 bar (rotary), 150 bar (reciprocating)
Shaft Speed	15 m/sec (rotary)
pH	1 to 14
Applications	Pumps, agitators, mixers etc